

IN625

Nickel-based alloy ideal for applications in aerospace and energy industries

Key Features:

- > Excellent heat and corrosion resistance
- > High tensile, creep and rupture strength
- > Good ductility

Example Applications:

- > Gas turbines in aerospace and energy industries
- > Racing applications
- > Marine engineering
- > Chemical industry

[Technical Data]

General Properties

Mechanical Properties

(As built)


Mechanical Properties ¹

(Heat treated)

Density <small>ISO3369</small>	≥8.40 g/cm ³
Tensile Strength <small>ISO6892-1</small>	≥950 MPa
Yield Strength <small>ISO6892-1</small>	≥680 MPa
Elongation after Fracture <small>ISO6892-1</small>	≥33 %
Vickers hardness <small>ISO6507-1</small>	≥260 HV5/15
Tensile Strength <small>ISO6892-1</small>	≥850 MPa
Yield Strength <small>ISO6892-1</small>	≥620 MPa
Elongation after Fracture <small>ISO6892-1</small>	≥35 %
Vickers hardness <small>ISO6507-1</small>	n/a

¹ For more information on heat treatment process, please contact us directly. Farsoon systems are open material platform. For special materials such as tungsten, tantalum and pure copper, please contact us with your inquiries or requirements.

Disclaimer: Many factors may affect the performance characteristics of products. We recommend that you make tests to determine the suitability of a product for your particular purpose prior to use. Farsoon makes no warranties of any type, express or implied, including but not limited to, the warranties of merchantability or fitness for a particular use. This also applies regarding the consideration of possible intellectual property rights as well as laws and regulations. Farsoon reserves the right to change the technical data without notice. Farsoon®, Buildstar®, Makestar® are registered trademarks of Farsoon Technologies. Last Change: 2022-01-29



Turbine Blade
System: FS273M

www.farsoon.com