

## FS3401GB-F

Developed for FLIGHT<sup>®</sup> Technology

Advanced PA12-based Glass Bead Reinforced Polymer Material

## Key Features:

- > Excellent mechanical strength and rigidity
- > Extraordinary dimensional stability
- > Good thermal/abrasive resistance

## **Example Applications:**

- > Perfect for functional end-use parts production
- > Ideal for industrial applications such as automotive engine system, electrical tools.

## [Technical Data]

General Properties	Bulk Density	0.65 g/cm <sup>3</sup>
	Part Density	1.30 g/cm <sup>3</sup>
	Color	Black
Thermal Properties	Melting Point (10°C/min) ISO 11357-1:2020	185.5 °C
	Heat Deflection Temp(HDT) @1.8 MPa ISO 78-1:2020	62 °C
	Heat Deflection Temp(HDT) @0.45 MPa ISO 78-1:2020	157 °C
Mechanical Properties	Tensile Strength ISO 527-1:2019	47 MPa
	Tensile Modulus ISO 527-1:2019	2810 MPa
	Elongation at Break ISO 527-1:2018	8.7%
	Flexural Strength ISO 178:2019	73 MPa
	Flexural Modulus ISO 178:2019	2550 MPa
	Izod Impact Strength (notched) ISO 180:2019	9.5 KJ/m <sup>2</sup>
	Izod Impact Strength (unnotched) ISO 180:2019	23 KJ/m <sup>2</sup>

Disclaimer: Many factors may affect the performance characteristics of products. We recommend that you make tests to determine the suitability of a product for your particular purpose prior to use. Farsoon makes no warranties of any type, express or implied, including but not limited to, the warranties of merchantability of fitness for a particular use. This also applies regarding the consideration of possible intellectual property rights as well as laws and regulations. Farsoon reserves the right to change the technical data without notice. Farsoon®, Buildstar®, Makestar® are registered trademarks of Farsoon Technologies. Last Change: 2022-01-29



www.farsoon.com

AMEA Farsoon Technologies Co., Ltd. | +86.731.8397.6198 | globalinfo@farsoon.com | No. 181 Linyu Road, Changsha National High-Tech Industrial Zone, Hunan, China AMERICAS Farsoon Americas CORP. |+1 512-551-9901 | info@farsoonam.com | 3161 Eagles Nest Street, Suite 350, Round Rock, TX 78665 EUROPE Farsoon Europe GmbH | +49 711 13796 0 | wehelpyou@farsoon-eu.com | Liebknechtstrasse 33, 70565 Stuttgart, Germany